

DECORATIVE FINISH

COLORFUL

UV RESISTANT

Solvent-free 2-component aliphatic resin for manual application (ratio: 2:1). Designed as a **UV-resistant** (non-yellowing) tinted topcoat over a SOUPLETHANE coating. Fast drying even at low temperatures. Easy and fluid to apply even at high humidity (up to 90%r.h).

Aesthetic and glossy finish.

CHARACTERISTICS

Nature chemical	Resin aliphatic 2-component	Mix Ratio	Comp. A / Comp. B = 2/1 a volume
------------------------	-----------------------------	------------------	----------------------------------

Solvent-free Dry Matter 100%

Packaging: 5 kg pre-dosed kits

Shelf life: 12 months - From the date of manufacture and in its original unopened packaging, under cover at more than 5°C in a cool, ventilated place (frost-free)

AVAILABLE COLOURS



Cream




Moka



light grey



dark grey



White

* Non-contractual colour chart
Samples on request

BENEFITS

- ✓ Finish perfectly adapted to SOUPLETHANE systems
- ✓ Does not yellow under UV radiation
- ✓ Solvent-free tinted finish
- ✓ Low power consumption
- ✓ Ease of application



KEMICA COATINGS

Reinventing coatings



bio-based



sustainable



eco-friendly

IMPLEMENTATION

PREPARATION OF THE MIXTURE

Carefully re-homogenize each component before mixing.

Mix well until you get an even shade. Add component B to component A. Knead mixture A + B with a mechanical stirrer for 40 sec. Then pour the product into a second container and continue mixing for 10 seconds. To minimise the entrainment of air and moisture during mixing, it is advisable to carry out this operation at a low speed (approx. 400 revolutions min.), taking care to keep the agitator at the bottom of the bucket during its rotation.

APPLICATION

Consumption: 300 g/m² to 500 g/m²

Thickness: 0.2 to 1 mm

POT LIFE 35 minutes

RECOVERY TIME

Mini : 5 h, Maxi : 72 h

DRYING TIME: 5 hrs

TDS and SDS available